

# TEST REPORT

**APPLICANT** : Xindao B.V.  
**ADDRESS** : P.O.Box 3082,2280 GB,Rijswijk,The Netherlands  
**SAMPLE DESCRIPTION** : Deluxe double wall electroplated glass mug  
**ITEM NO.** : P433.11  
**P.O. NO.** : PU036904  
**SAMPLE RECEIVED DATE** : 27-Jun-2022  
**TURN AROUND TIME** : 27-Jun-2022 to 04-Jul-2022

The following test item(s) was/were performed on submitted sample(s) and/or component(s) confirmed by applicant

TEST REQUESTED	RESULT
Leachable Lead and Cadmium	Pass

**Eurofins (Shanghai) contact information**

**Customer service:** [RickyFang@eurofins.com](mailto:RickyFang@eurofins.com)/ 36202991

**Sales specialist:** [WandyShen@eurofins.com](mailto:WandyShen@eurofins.com)/ +86 216 1819 181

\*\*\*\*\* FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) \*\*\*\*\*

Signed for and on behalf of  
Eurofins Product Testing Service (Shanghai) Co., Ltd




Jackson Zhou  
Chemical Lab Manager

*Samples are obtained by express delivery, Results obtained refer only to samples, products or material received in Laboratory, as described in point related to sample description, and tested in conditions shown in present report. Eurofins Product Testing Service (Shanghai) Co., Ltd ensures that this job has been performed according to our Quality System and complying contract and legal conditions. If you happen to have any comments, please do it by sending email to [info.sh@eurofins.com](mailto:info.sh@eurofins.com) and referring to this report number. Reproduction of this document is only valid if it is done completely and under the written permission of Eurofins Product Testing Service (Shanghai) Co., Ltd. If you happen to have any complaints, please do it by sending email to [chinacomplaint@eurofins.com](mailto:chinacomplaint@eurofins.com) and referring to this report number.*



**SAMPLE PHOTO(S)**



**EFSH22063525-CG-01**

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

### Leachable Lead and Cadmium

Test Requested : To determine the leachable Lead and Cadmium contents from the submitted samples with reference to European Council Directive 84/500/EEC (COUNCIL DIRECTIVE of 15 October 1984 on the approximation of the laws of the Member States relating to ceramic articles intended to come into contact with foodstuffs) and its amendment Commission Directive 2005/31/EC

Test Method : With reference to EEC Directive 84/500/EEC and 2005/31/EC. Analysis was performed by ICP-OES/ICP-MS.

### Category 2

Specimen	Vol. of 4% Acetic acid used (ml)	Depth (mm)	Diameter (mm)
	A	A	A
1	330	90	75
2	330	90	75
3	330	90	75
4	330	90	75

Specimen	Leachable Lead (mg/L)	Leachable Cadmium (mg/L)
	A	A
1	< 0.1	< 0.01
2	< 0.1	< 0.01
3	< 0.1	< 0.01
4	< 0.1	< 0.01
Limit	4.0	0.3

#### Notes:

- (1) Category 1: Articles that cannot be filled and articles that can be filled, the internal depth of which does not exceed 25 mm
- (2) Category 2: Articles, not in categories 1 or 3, which can be filled
- (3) Category 3: Cooking ware; packaging and storage vessels having a capacity of more than three liters
- (4) < = Less than

\*\*\*END OF THE REPORT\*\*\*